




PNRB37LS is 5 layer transparent BOPE film, HD additivated. One side heat sealable, one side non heat sealable corona treated suitable for printing.

Film density (0.937 g/cm³)



- PE printable layer, treated
- PE Intermediate layer
- PE core layer
- PE Intermediate layer
- PE heat sealable layer

TYPICAL APPLICATIONS

Rotogravure and flexo printing

Lamination

Single web as substitute of thicker blown PE film

Properties	Test Methods	Deviation	Typical Values				
Thickness, µm			20	25	30	35	40
Average thickness deviation, %		±	3	3	2.5	2.5	2.5
Yield, m ² /kg		± 5%	53.5	42.7	35.6	30.5	26.7
Unit weight, g/m ²		± 5%	18.7	23.4	28.1	32.8	37.5
Gloss (45°)	ASTM D 2457	≥	86				
Haze, %	ASTM D 1003	± 1	2.5	2.5	2.5	2.5	2.5
Coefficient of Friction*	ASTM D 1894	± 0.05	0.3				
Elmendorf Test MD, mN Tear Test TD, mN	ASTM D 1938	± 10%	< 500			< 500	
Tensile strength, MPa			80			210	
	MD TD	ASTM D 882	± 20				
Elongation at break, %			330			70	
	MD TD	ASTM D 882	± 30				
Shrinkage, % 100°C – 5 min	MD TD	Internal Method	± 1		3 5		
Seal strength, N/15 mm, 100°C, 1bar 1 sec **		Internal Method	≥	5	5	6	6
Sealing Initiation Temperature (SIT), °C **		Internal Method	82				
Surface treatment, dynes/cm	ASTM D 2578a		Min 38	Min 38	Min 38	Min 38	Min 38

*- Dynamic COF film/film, non-treated to non-treated side

**--Reported heat sealing properties on non-treated to non-treated film side

The specified values are based on average results, measured by the manufacturer during standard production. They should not be considered as Data Sheet of any particular product.

The end user should be satisfied as to the suitability of the product for the intended application and the present regulatory regime. Therefore Plastchim-T AD disclaims any liability for damages arising from the non-suitability of the product for the effected application.



FOOD CONTACT

The BOPE Film complies with all national and international standards and requirements for food contact. Declaration of Compliance is accessible at www.plastchim-t.com.

INDICATION OF PRINTABLE SURFACE

PNRB37S is usually supplied with printable layer on the outside surface, in case of requirement for printable layer inside, this must be agreed with our sales representative before order processing.

PACKING

	Core Diameter	Outer Diameter *	Notes
Vertical	152 mm (6`) 76 mm (3`)	≤ 550 mm	≤ 700 mm – two or more rows > 700 mm – one row
Horizontal	152 mm (6`) 76 mm (3`)	≤ 770 mm	

(*) In case of no other requirements

TOLERANCES

Weight tolerance, depending on the order volume	Width tolerance	Length tolerance
≤ 1 000 kg ± 20% 1001 ÷ 10 000 ± 10% >10 000 ± 5%	± 2 mm	±5 %

Storage and Transportation Terms & Conditions

Palletizing of goods is done according to customer's requirements.

The storage of all goods is in dry, covered and clean warehouses.

The transportation of the goods is carried out in dry, covered and clean means of transport.

The recommended temperature of storage/transportation is 10-30°C. If the temperature is not within the recommended limits, the following issues may occur:

- Decrease of dyne level
- Higher haze of the film
- Poor adhesion of the film surface that on a later stage could be an issue for laminating and printing
- Extremely low COF that can trouble further processing

Excessive humidity can be a reason for film blocking.

It is recommended that BOPE film should be tempered at operating room temperature for 24 hours before use.

Adherence to the above mentioned storage conditions ensures that the film is suitable to be used up to 6 months after production.

Claims regarding to the transportation are accepted within 1 week after the delivery date. If any, a record has to be taken in the CMR.

Last update: Edition 1 / 15th December 2022