


# COEXTRUDED BIAXIALLY ORIENTED PP FILM FOR TOBACCO WRAPPING - HIGH SHRINK

## **Description and Application**

- Both-side heat sealable
- Intended for tobacco products packaging (cigarette boxes, cartons bundle wrapping, cigars...) specially designed for wrinkle free hard packs cigarette - high shrink film
- Excellent optical properties (gloss, haze) and slip properties (tailored for high speed packers)
- Improved barrier properties (moisture, odor) and antiblocking properties





# TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES		
Nominal thickness	DIN 53370	μm	16	18	20
tolerance	טווע טאטע	%	+-5		
Unit weight		g/m²	14,8	16,5	18,2
tolerance	Internal method	%	+-5		
Yield		m²/kg	67,6	60,6	54,9
Tensile strength					
MD (min.)		$N/mm^2$		180	
TD (min.)				280	
Elongation at break	DIN EN ISO				
MD (max.)	527-1/3	%		150	
TD (max.)				65	
Elasticity modulus		N/mm²		2700	
MD (min.)		14/ 111111			
Water vapour	ASTM F 1249				
permeability (max.)	23°C, 85% r.h.	g/m².24h	1,6	1,5	1,4
	38°C.90% r.h.		3,5	3,2	3,0
Oxygen permeability (max.)	DIN 53380	cm3/m2.24h.	2200	2100	2000
	23%. 0% r.h.	0,1MPa	2200		
Dynamic coefficient					
of friction - film/film	ASTM D 1894	-		0,3	
out / out side					
Seal temperature range	Internal method	°C		105 - 135	
Seal strength (min.)	120°C, 1,0s, 0,3MPa	N/15mm		2,0	
Shrinkage					
MD (min.)	130°C. 15min.	%		13	
TD (min.)				13	
<b>Gloss</b> (20°) (min.)	ASTM D 2457	%		90	
Haze (max.)	ASTM D 1003	%	2,	5 3	,0

<sup>\*</sup> After production \* \* After storage \* \* \* Typical values

tatrafan.com Edition: January 2017



# COEXTRUDED BIAXIALLY ORIENTED PP FILM FOR TOBACCO WRAPPING - HIGH SHRINK

#### **HANDLING AND STORAGE**

The product does not present special safety requirements during handling and storage. In order to maintain their properties and to ensure good processability, the film should be stored avoiding high humidity and high temperature conditions. Do not exceed an ambient temperature of  $40^{\circ}$ C (transport temperature beetween (-20 + 30)°C and relative humidity of 80%. The product should be protect away from direct sunlight and heat (steam lines or other). Take measures against electrostatic discharges – the film will accumulate electrostatic charge of the web – it could by cause an electrical spark (ignition source). Keep away from source of ignition. Use with adequate ventilation.

#### General notes:

Do not handle or store near an open flame, sources of the heat orignition. Store in cool, dry area, away from direct heat or sunlight (Film for food packaging applications keep away from hazardous chemicals). Film properties are guaranteed for 6 month from the date of production.



	Bobbin				
AVT	Length (m)	Core diameter (mm)	Outside diameter (mm)		
16	4100				
18	3800	76,8	310		
20	3300				

\*Standard

### **ENVIRONMENT**

When disposed of under orderly conditions no environmental damage effects occur. During burning under free air conditions only CO2, CO and water arise. Does not contain additives based on heavy metals (Cd,PB,HG,Cr). This product is expected to persist.

### OTHER INFORMATION

This information and recommendation is based on Terichem's best knowledge and belief accurate and reliable as of the date indicated.

However, no representation, waranty or guarantee is made with regards to accuracy, reliability or completeness. Conditions of use of the material are under the control of the user, therefor it is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use.



tel.:+421 52 715 3285 fax:+421 52 715 2303 mail: sales@tatrafan.com