


COEXTRUDED BIAXIALLY ORIENTED PP FILM FOR TOBACCO WRAPPING

Description and Application

- Both-side heat sealable
 Intended for tobacco products packaging
 LOW SEALING TEMPERATURE
- Designed for bundle wrapping without carton paper ("naked" wrapping)
- Excellent optical properties (gloss, haze) and slip properties
- Improved barrier properties (moisture, odor) and antiblocking properties





TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES	
Nominal thickness	DIN 52270	μm	20	25
tolerance	DIN 53370 %	+-5		
Unit weight		g/m²	18,2	22,8
tolerance	Internal method	%	+-5	
Yield		m²/kg	54,9	43,9
Tensile strength				
MD (min.)		N/mm²	150	
TD (min.)			250	
Elongation at break	DIN EN ISO			
MD (max.)	527-1/3	%	15	50
TD (max.)			6	5
Elasticity modulus		N/mm²	2850	2450
MD (min.)		14/ 111111	2030	2430
Water vapour	ASTM F 1249			
permeability (max.)	23°C, 85% r.h.	g/m².24h	1,5	1,4
	38°C.90% r.h.		3,3	3,0
Oxygen permeability (max.)	DIN 53380	cm3/m2.24h.	2100 2000	
	23%. 0% r.h.	0,1MPa		
Dynamic coefficient				
of friction - film/film	ASTM D 1894	-	0,3	
out /out side				
Seal temperature range	Internal method	°C	75 - 130 2,0	
Seal strength (min.)	120°C, 1,0s, 0,3MPa	N/15mm	2	,U
Shrinkage				
MD (min.)	130°C. 15min.	%	9	
TD (min.)			10	
Gloss (20°) (min.)	ASTM D 2457	%	90	
Haze (max.)	ASTM D 1003	%	2,8	3,0

^{*} After production * * After storage * * * Typical values

tatrafan.com Edition: January 2017



COEXTRUDED BIAXIALLY ORIENTED PP FILM FOR TOBACCO WRAPPING

HANDLING AND STORAGE

The product does not present special safety requirements during handling and storage. In order to maintain their properties and to ensure good processability, the film should be stored avoiding high humidity and high temperature conditions. Do not exceed an ambient temperature of 40° C (transport temperature beetween (-20 + 30)°C and relative humidity of 80%. The product should be protect away from direct sunlight and heat (steam lines or other). Take measures against electrostatic discharges – the film will accumulate electrostatic charge of the web – it could by cause an electrical spark (ignition source). Keep away from source of ignition. Use with adequate ventilation.

General notes:

Do not handle or store near an open flame, sources of the heat orignition. Store in cool, dry area, away from direct heat or sunlight (Film for food packaging applications keep away from hazardous chemicals). Film properties are guaranteed for 6 month from the date of production.



	Bobbin		
LST	Core diameter	Outside diameter	
	(mm)	(mm)	
20, 25	76 (76,8) 152	max. 800	

*Standard

ENVIRONMENT

When disposed of under orderly conditions no environmental damage effects occur. During burning under free air conditions only CO2, CO and water arise. Does not contain additives based on heavy metals (Cd,PB,HG,Cr). This product is expected to persist.

OTHER INFORMATION

This information and recommendation is based on Terichem's best knowledge and belief accurate and reliable as of the date indicated.

However, no representation, waranty or guarantee is made with regards to accuracy, reliability or completeness. Conditions of use of the material are under the control of the user, therefor it is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use.



tel.:+421 52 715 3285 fax:+421 52 715 2303 mail: sales@tatrafan.com